



Accura[®] 25 plastic

for use with solid-state stereolithography (SLA[®]) systems

Simulate the properties and aesthetics of polypropylene with this accurate and flexible material.



APPLICATIONS

- Functional components for assemblies and mock-ups for:
 - Automotive styling parts — trim, fascia, and other components
 - Consumer electronic components
 - Toys
 - Snap fit assemblies
- Master patterns for RTV/silicone molding
- Replace CNC machining of polypropylene to produce short-run plastic parts
- Simulate injection molded parts
- Concept and marketing models

FEATURES

- Look and feel of molded polypropylene
- High flexibility with excellent shape retention
- Outstanding feature resolution and accuracy
- High production speed
- Fully developed and tested build styles

BENEFITS

- Increased market opportunities for models
- Reliable and robust functional prototypes
- Suitable for master patterns
- More parts and better system utilization
- Maximize reliability with no user R&D

Accura[®] 25 plastic

For use with all solid-state stereolithography (SLA[®]) systems

"After providing some models in Accura 25 to a couple of our regular customers, they have decided to make it their default SL material for all future orders. To date they have already ordered hundreds of parts. They get a material that looks like a final article molded part having a great balance of durability and flexibility. I get a material that is very easy to clean and finish, but most importantly is extremely reliable in the machine. This has been a real win-win for us.."

— Steve Grundahl — Owner, Midwest Prototyping LLC

TECHNICAL DATA

Liquid Material

MEASUREMENT	METHOD/CONDITION	VALUE
Appearance		White
Liquid Density	@ 25 °C (77 °F)	1.13 g/cm ³
Solid Density	@ 25 °C (77 °F)	1.19 g/cm ³
Viscosity	@ 30 °C (86 °F)	250 cps
Penetration Depth (Dp) *		4.2 mils
Critical Exposure (Ec) *		10.5 mJ/cm ²
Tested Build Styles		FAST™, EXACT™, Exact HR

Post-Cured Material

MEASUREMENT	METHOD/CONDITION	METRIC	U.S.
Tensile Strength	ASTM D 638	38 MPa	5,450 - 5,570 PSI
Tensile Modulus	ASTM D 638	1,590 - 1,660 MPa	230 - 240 KSI
Elongation at Break (%)	ASTM D 638	13 - 20 %	
Flexural Strength	ASTM D 790	55 - 58 MPa	7,960 - 8,410 PSI
Flexural Modulus	ASTM D 790	1,380 - 1,660 MPa	200 - 240 KSI
Impact Strength (Notched Izod)	ASTM D 256	19-24 J/m	0.4 ft- lb/in
Heat Deflection Temperature	ASTM D 648		
	@ 66 PSI	58 - 63 °C	136 - 145 °F
	@ 264 PSI	51 - 55 °C	124 - 131 °F
Hardness, Shore D		80	
Co-efficient of Thermal Expansion	ASTM E 831-93		
	TMA (T<T _g , 0 - 20 °C)	107 x 10 ⁻⁶ m/m °C	
	TMA (T>T _g , 90 - 150 °C)	151 x 10 ⁻⁶ m/m °C	
Glass Transition (T _g)	DMA, E''	60 °C	140 °F

* Dp/Ec values are the same on all systems.



SYSTEMS

TRANSFORM YOUR PRODUCTS

3D Systems Corporation
333 Three D Systems Circle
Rock Hill, SC 29730 U.S.A.

Tel: 803.326.4080
Toll-free: 800.889.2964
Fax: 803.324.8810

moreinfo@3dsystems.com
www.3dsystems.com
NASDAQ: TDSC

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2007 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. The 3D logo, Accura and SLA are registered trademarks of 3D Systems, Inc.

PN 70668 Issue Date - 06 Sep 07